

EPR POWER CABLE 5000/8000 VOLTS

Single Conductor, Shielded, 5000 Volts - 133% or 8000 volts - 100% Insulation Level
 AEIC CS8, MV-105, Sunlight Resistant, CT Use


APPLICATION: As medium voltage MV-105 power cable for use in main feeder, distribution and branch circuits in industrial, commercial and electric utility installations. Cables may be used in wet or dry locations in circuits not exceeding 5000 volts 133% insulation level or 8000 volts 100% insulation level, at conductor temperatures not exceeding 105°C for normal, 140°C for emergency overload and 250°C for short-circuit conditions. Suitable for installation in conduit, tray, trough, ducts, aerial and direct burial applications.

STANDARDS:

1. Conforms to ICEA S-93-639, NEMA WC74 for 5-46 kV Shielded Power Cable.
2. Conforms to ICEA S-97-682 for Utility Shielded Power Cables Rated 5 Through 46 kV.
3. Conforms to AEIC CS8 for Extruded Dielectric, Shielded Power Cables Rated 5 Through 46 kV.
4. Listed by UL as Type MV-105, per Standard 1072.
5. Listed by UL as Sunlight Resistant.
6. Listed by UL For CT Use (1/0 and larger).
7. Conforms to Federal Specification J-C-3013.

CONSTRUCTION: Annealed copper conductor, extruded conductor shield, EPR ethylene-propylene-rubber insulation, extruded insulation shield, 5 mil copper shielding tape, black polyvinyl chloride jacket, surface printed.

OPTIONAL JACKETS: CPE, HYPALON® , LSZH (Low Smoke Zero Halogen)



	Size AWG or kcmil	No. of Strands	Thickness in Mils		Nominal Diameter Over Ins. Inches	Nominal Diameter Inches	Copper Conductor				
			Insulation	Jacket			Approx. Net Wt. lbs/1000 ft	Copper Weight lbs/1000 ft	Ampacity*		
									Tray	Conduit	Duct
5000 VOLTS - 133% INSULATION LEVEL (Ungrounded Neutral or 8000 VOLTS - 100% INSULATION LEVEL (Grounded Neutral))											
4-015KVESP	4	7	115	60	.50	.71	350	178	-	110	120
2-015KVESP	2	7	115	60	.56	.77	460	259	-	145	155
1-015KVESP	1	19	115	60	.60	.81	565	315	-	175	180
1/0-015KVESP	1/0	19	115	60	.64	.84	620	386	290	200	210
2/0-015KVESP	2/0	19	115	80	.68	.93	755	474	330	225	235
3/0-015KVESP	3/0	19	115	80	.73	.99	890	585	385	270	270
4/0-015KVESP	4/0	19	115	80	.79	1.04	1055	725	445	305	310
250-015KVESP	250	37	115	80	.85	1.09	1205	849	495	355	345
350-015KVESP	350	37	115	80	.95	1.20	1570	1165	615	430	415
500-015KVESP	500	37	115	80	1.08	1.34	2115	1639	775	530	505
750-015KVESP	750	61	115	80	1.27	1.53	2995	2427	1000	665	630
1000-015KVESP	1000	61	115	80	1.42	1.68	3870	3210	1200	770	720

TRAY: Single layer in uncovered cable tray with one cable diameter spacing, 105°C Conductor Temperature, 40°C Ambient. CONDUIT: Three cables in isolated conduit in air, 105°C Conductor Temperature, 40°C Ambient. DUCT: Three cables per duct, 105°C Conductor Temperature, 20°C Ambient, One Circuit, 100% Load Factor, Rho = 90. For other installation conditions refer to the NEC.

Specification

EPR POWER CABLE, 5000/8000 VOLTS

Single Conductor, Shielded, 5000 Volts -133% or 8000 Volts - 100% Insulation Level
AEIC CS8, MV-105, Sunlight Resistant, CT Use

1. SCOPE

- 1.1 This specification describes single conductor, EPR (Ethylene-propylene-rubber) insulated, shielded power cables for use in circuits not exceeding 5000 volts 133% insulation level or 8000 volts 100% insulation level at conductor temperatures of 105°C for continuous normal operation, 140°C for emergency overload conditions and 250°C for short-circuit conditions. Cables are intended for power cable applications, in wet or dry locations including conduit, cable tray, duct, direct burial and aerial installation.

2. STANDARDS

- 2.1 The following standards shall form a part of this specification to the extent specified herein:
 - 2.1.1 ICEA Pub. No. S-93-639, NEMA Pub. No. WC74 for 5-46 kV Shielded Power Cable.
 - 2.1.2 ICEA Pub. No. S-97-682 for Utility Shielded Power Cables Rated 5 Through 46 kV.
 - 2.1.3 AEIC CS8 for Extruded Dielectric, Shielded Power Cables Rated 5 Through 46 kV.
 - 2.1.4 UL Standard 1072 for Type MV-105.

3. CONDUCTORS

- 3.1 Class B stranded annealed uncoated copper per Part 2 of ICEA.

4. CONDUCTOR SHIELDING

- 4.1 Conductors shall be covered with a layer of extruded conducting thermosetting compound with thickness in accordance with Table 3-1 of ICEA S-97-682. The extruded layer shall be compatible with and firmly bonded to the cable insulation and shall be in accordance with Par. 3.1 and meet the resistivity requirements of Par. 3.6.1 of ICEA S-97-682.

5. INSULATION

- 5.1 Directly over the conductor shielding shall be applied a homogeneous wall of EPR insulation. The insulation thickness shall be 115 mils and the minimum thickness at any point shall be not less than 90% of the specified thickness. Physical and electrical properties of the insulation shall be in accordance with Part 4 of ICEA S-97-682 for a Class III Insulation.

6. SHIELDING

- 6.1 Over the insulation shall be applied an extruded conducting thermosetting insulation shield. It shall be in intimate contact with the outer surface of the insulation and shall be free-stripping, leaving no conducting particles or other residue on the insulation surface. This layer shall be legibly identified as being conducting. The thickness of this layer shall be in accordance with Table 5-1 of ICEA S-97-682. The insulation shield shall meet the requirements of Par. 5.5.1 of ICEA S-97-682.
- 6.2 Directly over the extruded insulation shield shall be a helically applied 5 mil uncoated copper shielding tape with a minimum lap of 12.5%. This tape shall meet the requirements of Part 6 of ICEA 8-97-682.

7. JACKET

- 7.1 A polyvinyl chloride jacket shall be applied overall. The jacket shall meet the requirements of Part 7 of ICEA S-97-682 and UL 1072. The jacket shall meet the Sunlight Resistant requirements of UL Standard 1072. The jacket thickness shall be as specified in Part 7 of ICEA S-97-682 and UL 1072. The minimum thickness at any point shall be not less than 80% of the specified UL thickness.

8. IDENTIFICATION

- 8.1 All cable shall be identified by means of surface ink printing indicating manufacturer, size, insulation type, insulation thickness, voltage rating, insulation level, year of manufacture and UL designations.

9. TESTS

- 9.1 Cable shall be tested in accordance with ICEA S-97-682, ICEA S-93-639, AEIC CS8 and UL Standard 1072.